

MEDIUM AND HEAVY WALL TUBING

S3 Medium Wall Flame Retardant Heat Shrink Tube

Flame retardant medium wall tubing formulated for wet and underground service on vessels platforms shipyards and harbours



Voltage Range	1 kV to 36 kV
Operating Temperature	-55 to 110 °C
Full Recovery Temperature	135 °C minimum
Shrink Ratio	3:1 and 4:1
Compliance	Flame retardant and RoHS
Environment	Wet and underground service

Introduction

Medium wall flame-retardant polyolefin shrink tubing,with or without adhesive liner.Excellent insulation,mechanical protection and sealing for outdoor electrical equipment and connections in wet and underground environments such as marine vessels,off-shore oil platform,shipyard and harbor applications.

Features

- Operating temperature: -55 to 110°C
- Minimum fully recovery temperature: 135°C
- Shrink ratio: 3:1 & 4:1
- Environmental friendly, RoHS compliant, Flame-retardant
- Single or Dual wall optional
- Standard Color: Black, Other colors optional
- Voltage class: 1kV ~ 36kV
- Thick-wall and halogen-free versions are also supplied
- Equivalent to TE BSTS-FR, SST-FR

Technical Data

Property	Test Method	Requirement
Tensile Strength	ASTM D2671	≥10.4 MPa
Ultimate Elongation	ASTM D2671	≥300%
Heat Aging (158°C/168h) Tensile Strength Ultimate Elongation	ASTM D2671	≥7.3 MPa ≥200%
Water absorption (23°C/24h)	ASTM D2671	≤0.5%
Low-temperature flexibility (-55°C/4h)	ASTM D2671	No cracking
Heat shock (200°C/4h)	ASTM D2671	No cracking, dripping or flowing
Dielectric strength	ASTM D2671	≥15 kV/mm
Volume resistivity	ASTM D2671	≥1.0×10 ¹⁴ Ω·cm
Flammability	UL224	VW-1

Dimensions

Size S3	As supplied(mm) Inner diameter D (min.)	After recovered (mm) Inner diameter d (max.)	Wall thickness t (nom.)	Standard length (m)
8/2	8	2	1.7(with glue)	1.0/1.22
9/3	9	3	1.8(with glue)	1.0/1.22
12/4	12	4	2.2(with glue)	1.0/1.22
16/5	16	5	2.5(with glue)	1.0/1.22
19/6	19	6	2.4	1.0/1.22
22/6	22	6	2.4	1.0/1.22
25/8	25	8	2.5	1.0/1.22
28/6	28	6	2.9	1.0/1.22
33/8	33	8	2.9	1.0/1.22
35/12	35	12	2.6	1.0/1.22
40/12	40	12	2.7	1.0/1.22
45/13	45	13	2.8	1.0/1.22
55/16	54	16	2.9	1.0/1.22
65/19	65	19	2.9	1.0/1.22
75/22	75	22	2.9	1.0/1.22
85/25	85	25	2.9	1.0/1.22
95/25	95	25	3.3	1.0/1.22
115/34	115	34	3.3	1.0/1.22
130/36	130	36	3.4	1.0/1.22
140/42	140	42	3.4	1.0/1.22
160/50	160	50	3.5	1.0/1.22
175/58	175	58	3.5	1.0/1.22
200/65	200	65	3.6	1.0/1.22
230/75	230	75	3.6	1.0/1.22
260/85	260	85	3.6	1.0/1.22

Cross Reference

Tyco-Raychem: BSTS-FR/SST-FR

Enquiries • enquiry@upolymer.com • WhatsApp +86 159 4096 9469 • Dalian United Polymer Material Co., Ltd., Shihe Industrial Park, Puwan New District, Dalian Liaoning 116101 China